

KEY URECON CV

Product Data Sheet



DESCRIPTION

KEY URECON CV is a heavy duty, trowel applied urethane modified cementitious topping formulated for vertical applications. **KEY URECON CV**'s high impact resistance and excellent thermal shock and chemical resistance make it ideal for heavy manufacturing and food processing areas. **KEY URECON CV** is a moisture vapor tolerant system making it the ideal solution for many moisture problems. **KEY URECON CV** may be used both indoors and outdoors and in areas where freeze/thaw is a factor. Excellent for forming cove base, cants and trench linings, **KEY URECON CV** is the key choice for wet areas, dairies, food processing areas, and industrial kitchens. Note: **KEY URECON CV** is not color stable unless a UV light resistant topcoat is used, refer to **KEY URECON SLT** for various color stable topcoat options.

KEY ADVANTAGES

- High impact, thermal shock, and wear resistance
- Excellent chemical resistance
- Low odor for use in occupied areas
- Meets USGBC LEED criteria for low VOC
- Hygienic—will not support growth of fungus or bacteria
- Unaffected by moisture vapor transmission for on or below grade applications
- Meets USDA requirements for incidental food contact
- Rapid one step application for fast return to service

KEY CONSIDERATIONS

- Should be applied when temperature is between 50°F and 85°F
- Site must be free from condensation or water contamination during application and cure
- Substrate should be clean, dry, sound, properly prepared concrete
- Material requires mechanical mixing. Do not mix partial units
- Movement of substrate cracks may transmit through system

COLOR SELECTION

Refer to **Key Dry Oxide Pigment Colors Chart**. Price surcharge for Blue, Green, Safety Yellow. May also use **Key Urethane Pigment Packs** at additional cost. Light colors will become altered with exposure to UV spectrum light.

CURE/DRY TIME

Working Life	10-15 mins @ 75°F, 50% RH
Recoat* (*Accelerator Additive reduces time)	6-8 hrs @ 75°F, 50% RH
Light Foot Traffic Service	8-10 hrs @ 75°F, 50% RH
Light Vehicular Traffic	12-16 hrs @ 75°F, 50% RH
Full Cure & Max. Resistance	3-5 days @ 75°F, 50% RH

APPLICATION

SURFACE PREPARATION

Surface Preparation is the most critical portion of any successful resinous flooring system application. All substrates must be properly prepared as outlined in **Key Resin Technical Bulletin #1**. **KEY URECON CV** may be installed over 5 day old concrete. **Important:** Be aware that concrete substrates will continue to contract (shrink) during early cure stage possibly causing random shrinkage cracks in the concrete or covered contraction (sawcut) joints to crack, resulting in reflective cracks in the **KEY URECON CV** topping—contact Key Resin Technical Service for recommendations.

Concrete substrates should be a minimum of 3000 psi compressive strength and 225 psi tensile strength. Substrates should be sloped to drain in wet areas to prevent standing water or chemicals.

Work must be performed by experienced contractors. The **Key Resin Technical Service Department** is available to answer any questions.

MIXING INSTRUCTIONS

Mechanical mixing is required. Add Part I and Part II in running mixer and blend until uniform (about 30 seconds). Add oxide pigment pack and Part III aggregate slowly to mix and blend for 1 more minute. Use immediately.

INSTALLATION

KEY URECON CV is installed using a steel cove trowel or flat trowel depending on the application. Refer to detailed installation instructions document and **Key Resin Technical Service** for additional important details.

CLEAN UP

Clean skin with soap and water. Tools and equipment should be cleaned with xylene or lacquer thinner. Consult Safety Data Sheet (SDS) for safety and health precautions.

KEY URECON CV

Product Data Sheet



TECHNICAL DATA

Mixing Ratio	Pre-Packaged Kit
Weight (liquids)	9.00-9.50 lbs per gallon, mixed
Volatile Organic Content (VOC) (EPA Method 24)	<5 g/L, compliant to low VOC Rule 1113 in all 50 states

AVAILABILITY

Key Resin materials are available throughout the United States and a number of other countries. Contact the **Key Resin Representative** in your area for details.

TECHNICAL SERVICE

Key Resin Company provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces. **Key Resin Sales/Technical Representatives** are available to assist you. Telephone 888.943.4532 or visit www.keyresin.com.

PHYSICAL PROPERTIES

Compressive Strength	ASTM C579	7,500 psi
Tensile Strength	ASTM C307	800 psi
Flexural Strength	ASTM C580	2,000 psi
Fungus and Bacteria Growth	MIL-F-52505 § 4.4.2.11	Will not support growth of fungus or bacteria when subjected to mildew and bacteria tests
Thermal Coefficient of Expansion	ASTM C531	1×10^{-5} in/in/per °F
Impact Resistance	MIL-F-3134J	Withstands 16 ft./lb. without cracking, delamination, or chipping
Modulus of Elasticity	ASTM C469	1.7×10^5 psi
Adhesion to Concrete	ASTM D7240	300-400+ psi (Concrete Failure, varies by concrete strength)
Service Temperature Resistance		-50 – 240°F wet, 280°F wet intermittent, 350°F dry
Thermal Shock Resistance	ASTM C884	Passes

WARRANTY

Key Resin Company ("Key") warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed, and applied in accordance with recommendations of Key. If any product fails to meet this warranty, the liability of Key will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Key within (1) one year of delivery of materials. Key may in its discretion refund the price received by Key in lieu of replacing the material. No customer, distributor, or representative of Key is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Key. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Key reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. KEY'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND KEY SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Rev 3/20/2025 v1.1