KEY #625 CHEMICAL RESISTANT EPOXY

Product Data Sheet



DESCRIPTION

KEY #625 is a high performance, chemical resistant, two component pigmented epoxy resin. The modified Bisphenol F and novolac chemistry of **KEY #625** is recommended wherever a high build, acid and alkali resistant, protective industrial maintenance floor finish is required. It is essentially odorless and can be used in occupied areas. **KEY #625** provides a smooth, high gloss finish or with added grit a textured finish, and is used as a finish coating for various **Key Resin Systems** with a "-**HP**" (High Performance) designation.

KEY ADVANTAGES

- Easy application
- · Superior chemical and stain resistance
- · Low odor for use in occupied areas
- Meets VOC criteria for industrial maintenance coating
- Meets USDA requirements
- Suitable for wet process flooring applications

KEY CONSIDERATIONS

- Substrate temperature must be a minimum of 50°F
- Substrate must be free of dirt, waxes, curing agents and other foreign materials
- Not recommended for immersion in oxidizing agents or mineral acids
- · Concrete must be properly prepared

COLOR SELECTION

KEY #625 is available in **Key Resin Standard Colors** and custom colors with lab approval, longer lead time and possible added cost.

COMPOSITION

100% solids epoxy and novolac epoxy resin, modified cycloaliphatic amines and fillers.

COVERAGE

KEY #625 will yield approximately 10-16 mils when spread at 100-160 ft² per gallon. Coverage rate varies by type of system. Do not apply less than 10 mils to achieve proper hiding power and leveling characteristics.

CURE/DRY TIME

Working Life	20-25 min. @ 75°F
Dry to Touch	6-8 hrs @ 75°F
Recoat	12-16 hrs @ 75°F
Light Foot Traffic Service	24 hrs @ 75°F
Full Cure & Max. Resistance	5 Days

APPLICATION

SURFACE PREPARATION

Surface Preparation is the most critical portion to any successful resinous flooring system application. All substrates must be properly prepared as outlined in **Key Resin Technical Bulletin #1**. Work must be performed by trained or experienced contractors or maintenance personnel. Contact the **Key Resin Technical Service Department** with questions.

INSTALLATION

KEY #625 will vary with type of system and application method. For complete installation instructions, contact **Key Resin Technical Service**.

CLEAN UP

Clean skin with soap and water. Tools and equipment should be cleaned with xylene or lacquer thinner. Consult Safety Data Sheet (SDS) for safety and health precautions.

KEY #625 CHEMICAL RESISTANT EPOXY

Product Data Sheet



TECHNICAL DATA

Mixing Ratio	2 Parts A:1 Part B by Volume
Solids Content	98% Solids by Volume
Volatile Organic Content (VOC) (EPA Method 24)	<100 g/L, compliant to Industrial faintenance Coating VOC Rule 1113
Weight/gal	11.5 lbs/gal, Mixed
Viscosity @ 75°F	1,000 cps

AVAILABILITY

Key Resin materials are available throughout the United States and a number of other countries. Contact the **Key** Resin Representative in your area for details.

TECHNICAL SERVICE

Key Resin Company provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces. Key Resin Sales/Technical Representatives are available to assist you. Telephone 888.943.4532 or visit www.keyresin.com.

MAINTENANCE

WARRANTY

After completing the application of KEY #625, the installer should provide the owner with maintenance instructions. KEY #625 is easily cleaned with neutral soaps or detergents. Refer to Key Resin Technical Bulletin #3 and #3A for additional recommendations.

CHEMICAL RESISTANCE

REAGENT	RATING
Acetic Acid - 5%	R
Acetone	L
Ammonia Hydroxide - 38%	L
Beer	R
Bleach - 10%	L*
Brake Fluid	R
Citric Acid - 30%	R
Citric Acid - 40%	L
Crude Oil	R
Diesel Fuel	R
Ethylene Glycol	R
Fatty Acids	L
Gasoline	R
Hydrochloric Acid - 15%	R
Lactic Acid - 15%	R
Lactic Acid - 50%	L
Methyl Ethyl Ketone	L
Nitric Acid - 10%	R*
Orange Juice	R
Peroxide - 35%	L
Phosphoric Acid - 85%	L
Skydrol	R
Sodium Hydroxide - 50%	R
Sulfuric Acid - 20%	R*
Toluene	L
Urea	R
Vinegar	L
Xylene	L

R - Recommended for splash/spill service with daily cleanup.

exposure time increases the concentration and reactivity of the reagent.

Refer to Key Resin Chemical Resistance Guide for further information.

Key Resin Company ("Key") warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed, and applied in accordance with recommendations of Key. If any product fails to meet this warranty, the liability of Key will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Key within (1) one year of delivery of materials. Key may in its discretion refund the price received by Key in lieu of replacing the material. No customer, distributor, or representative of Key is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Key. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Key reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANT-ABILITY OR FITNESS FOR PURPOSE. KEY'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND KEY SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Rev 6/12/2025 v2.1

L - Limited recommendation for 8 hours or less exposure time, requires more frequent cleanup, occasional spills only.
*May cause slight stain or discoloration depending on exposure time. Increase in